

FLXTITE V-520BB PVC SHRINK FILM TYPICAL PROPERTIES

FLXTITE V-520BB: A preferential shrink PVC film specifically designed for carpet and remnant belly band wrapping. Its high clarity and excellent tensile and elongation properties make it an ideal film for automatic broadloom and carpet overwrap.

TYPICAL PROPERTIES	UNITS	VALUE	VALUE	VALUE	ASTM TEST
GAUGE		125	150	200	
YIELD	sq.in./lb	17,650	14,950	11,100	
ROLL WEIGHT		1.7	1.7	1.7	
HAZE	%	1.2	1.2	1.6	D-1003
FREE SHRINK @150 F	%	MD TD	MD TD	MD TD	D-2732
		15/0	15/0	15/0	
TENSILE STRENGTH	psi	MD TD	MD TD	MD TD	D-882
		7300 / 5000	7400 / 5000	7600 / 5100	
ELONGATION AT BREAK	%	MD TD	MD TD	MD TD	D-882
		215 / 400	215 / 440	220 / 450	
SEAL RANGE	farenheit	350-390	350-390	350-390	
WVTR	g/100sq.in./24hr	12	11	8	E-96
OXYGEN	cc/100sq.in./24hr		750		D-3985
CO2	cc/100sq.in./24hr		7500		
STORAGE TEMPERATURE	farenheit	BELOW 75 DEGREES			
SINGLEWOUND ROLL LENGTHS	feet per roll	2500	200	1500	
AVAILABILITY					
SINGLEWOUND ROLL WIDTHS	inches	3" - 48"			

NOTE: All PVC Shrink Films must be stored at temperatures of no more than 75 degrees farenheit.

The above values are based on test data believed to be reliable. This data, however, is merely a guide and should not take the place of through testing for each intended use.

SELLER MAKES NO WARRANTY, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE except that the product shall conform to contracted specifications, and that the product does not infringe any valid United States patent.

The Buyer assumes the sole responsibility to determining the suitability of the product for the uses and applications contemplated by Buyer and others. Furthermore, the Buyer assumes all risk and liabilities for results obtained by the use of the product, whether used singularly or in combination with other material, except those relating solely to the use of the product not conforming to the contracted specifications, which non-conformity is not discoverable by Buyer or others. Any suggestion or recommendations made by the Seller concerning uses or applications of the product are believed to be reliable, but Seller makes no warranty or guarantee of results obtained since the condition of the use and application by Buyer and others are beyond Seller's control.